

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
30 June 2005 (30.06.2005)

PCT

(10) International Publication Number
WO 2005/059211 A1

(51) International Patent Classification⁷:

D01F 6/60

(74) Agent: HEIMANN, Anette; CPW GmbH, Kasinostrasse 19-21, 42103 Wuppertal (DE).

(21) International Application Number:

PCT/EP2004/013542

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date:

30 November 2004 (30.11.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

03028091.1 9 December 2003 (09.12.2003) EP

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (for all designated States except US): TEIJIN TWARON B.V. [NL/NL]; Westervoortsedijk 73, NL-6827 AV Arnhem (NL).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2005/059211 A1

(54) Title: ARAMID FIBRILS

(57) **Abstract:** The invention relates to aramid fibrils having in the wet phase a Canadian Standard Freeness (CSF) value less than 100 ml, after drying a specific surface area (SSA) less than 7 m²/g, and a weight weighted length for particles having a length > 250 µm (WL 0.25) less than 1.2 mm, and to a method of preparing the fibrils comprising the steps a. polymerizing an aromatic diamine and an aromatic dicarboxylic acid halide to an aramid polymer, in a mixture of N-methylpyrrolidone or dimethyl- acetamide and calcium chloride or lithium chloride to obtain a dope wherein the polymer is dissolved in the mixture and the polymer concentration is 2 to 6 wt. %, b. converting the dope to fibrils by using a jet spin nozzle under a gas stream, and c. coagulating the fibrils using a coagulation jet.